

Uncoated Papers

Toner
Water
(eco) Solvent
UV Curable
Latex

LFM054 Red Label Paper - PEFC

75 g/m²

Product Description Quality paper with low chlorine content and high whiteness. Excellent for use where the quality of your documents must reflect the image of your work and organisation.

Physical Properties	Weight (g/m ²)	75	ISO 536	Opacity (%)	93	ISO 2471
	Bulk (cm ³ /g)	1.36	ISO 534	Roughness (ml/min)	220	ISO 8791-2 Bendtsen
	CIE Whiteness (%)	164.0				

Applications/features High quality drawings and posters
 ISO 9706 standard for permanence
 EMAS and ISO 14001 certified
 PEFC Chain-of-Custody
 EU Ecolabel

Available Widths (mm)	3"core	210	297	420	594	620	841	914	1067		
	Refer for our current offering to mediaguide.oce.com										

Storage Conditions Shelf life: 2 years, Temperature 21°C, Relative Humidity 50%.
 Repack opened rolls when not in use. Allow material to adapt to room conditions for 24 hours before printing.

Print Conditions Best results are obtained between 20-27°C and 30-60% RH.

Environment, Health & Safety No Material Safety Data Sheet required. Paper waste suitable for recycling.

Lamination Compatibility	Cold	Warm	Hot	Cold: pressure sensitive Warm: heat activated: 85°C - 95°C Hot: heat activated: 105°C -130°C
	yes	yes	yes	

Outdoor Use Developed for indoor use.

Colour Profiles Canon develops high-quality colour profiles for media / ink / printer / RIP combinations. Check availability of profiles for your printer on mediaguide.oce.com

Environmental
Certification



Processing
Guidelines

Printing guidelines

Allow material to adapt to room conditions for 24 hours before printing.

It is recommended to handle the media with cotton gloves. Make sure that the media does not come into contact with grease, oil, silicon, and dirt to avoid printing defects.

Insert media with care in the printers. Incorrect loading can cause skewing or creasing. Allow material to adapt to room conditions for 24 hours before printing. It is recommended to calibrate the printer before printing and to make a test print. Print results will vary for different printers.

Ink/toner restrictions and printer settings have to be set for specific printers to obtain the best results. Canon colour profiles include recommended ink restrictions and printer settings for Canon supported printers.

Finishing guidelines

When laminating Océ CrystalPoint® prints pressure sensitive laminates are recommended.

A laminator with soft rubber rollers is preferred.

For optimal results temperature should be set between 55-60°C.

Standard disclaimer:

All specifications subject to change without notice. All company and/or product names are trademarks and/or registered trademarks of their respective manufacturers in their markets and/or countries.